

Hempel's Exterior Filler

(Formerly known as Contex Exterior Filler)

Product characteristics

Description

Hempel's Exterior Filler is a high-grade, waterborne acrylic filler. It has excellent workability and filling properties. Mainly used for leveling surface imperfections for exterior, can also be used in filling joints in gypsum boards, also as a touch-up filler for local surface imperfections or for full skim-coat application.

Recommended use

Hempel's Exterior Filler is ideal as filler for exterior surfaces like walls, ceilings, partitions, etc.

Features

- Excellent workability.
- Outstanding filling properties.
- Receives emulsion & enamel topcoat.
- Serves from a skim-coat to touch ups.

Product safety

Flash point 100°C [212°F]

VOC content

Legislation	Value
EU	21 g/L [0.18 lb/US gal]
US (coatings)	21 g/L [0.18 lb/US gal]
US (regulatory)	40 g/L [0.33 lb/US gal]

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

38900

Standard shade / code

Off white 11630

Gloss

Dead matt

Volume solids

54 ± 2%

Specific gravity

1.8 kg/L [15 lb/US gal]

Reference dry film thickness

200 micron [7.9 mils]

Surface preparation

Cleanliness

- The surface must be dry and clean prior to application.

New build:

- Concrete must cure completely; for 28 days minimum.
- Moisture content in the surface must be below 4%.

Maintenance and Repair

- Remove dust, loose material and any other contamination.
- Apply primer/sealer prior to application of filler.
- Areas with filler to be sealed with primer/sealer.

Roughness

- Sand to smoothen filler.

Consult Hempel's separate Surface Preparation Guidelines for more details.

Hempel's Exterior Filler

(Formerly known as Contex Exterior Filler)

Application

Cleaner

Fresh water

Application method

Tool	Application parameters
Putty knife	Not Applicable.
Trowel	Not Applicable.
Smooth metallic spatula	Not Applicable.
Thinning is not allowed.	

Film thickness

	High	Recommended
Dry film thickness	200 micron [7.9 mils]	200 micron [7.9 mils]
Wet film thickness	370 micron [15 mils]	370 micron [15 mils]
Theoretical spreading rate	2.7 m ² /L [110 sq ft/US gal]	2.7 m ² /L [110 sq ft/US gal]

Application conditions

- Surface temperature must be above 5 °C [41°F] during application and curing.
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Provide adequate ventilation during application and drying.

Relative Humidity:

- Relative humidity must be below 75 % during drying and curing.

Application remarks

- Stir well before use.
- The practical consumption factor may vary depending on application conditions, equipment and workmanship.

Drying and overcoating

Product compatibility

- Previous coat: Recommended products are: Sealing/ Priming: Topaz WB Primer, Hempel's WB Primer, Contex SB Primer or as specified.

Drying time

Surface temperature		20°C [68°F]	10°C [50°F]	40°C [104°F]
Surface dry	hours	2	4	1
Through dry	hours	6	10	4
Ready to sand	hours	6	-	-

Determined for dry film thickness 200 micron [7.9 mils] at standard conditions, see Hempel's Explanatory Notes for details. Any masking tape used during paint application should be removed while the paint is still in the wet condition.

Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]	40°C [104°F]
Atmospheric mild				
Topaz Primer	Min	16 h	8 h	4 h
	Max	Ext*	Ext	Ext
Contex Topcoat Matt	Min	16 h	8 h	4 h
	Max	Ext*	Ext	Ext

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

Overcoating details

- The surface must be dry and clean prior to application.

Hempel's Exterior Filler

(Formerly known as Contex Exterior Filler)

Storage

Shelf life

Ambient temperature	25°C [77°F]
Product	12 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.

Storage conditions

- Product must be stored according to local legislation, at maximum 40°C [104°F], without direct sunlight and protected from rain and snow.
- Temperature must not go below 0°C [32°F] during transport and storage.

Carbon Footprint

Dry film thickness	1 µm	1 mil
GWP (Global Warming Potential)	1.3 g CO₂e/m²	0.007 lb CO₂e/ft²

The carbon footprint is for 1 square meter / square foot of surface area with a dry film thickness of 1 micron / mil.

The scope includes raw materials, in-bound transport to the Hempel factory, Hempel manufacturing processes, and any Volatile Organic Compounds emitted during and after the application of the product.

It is calculated based on the standard shade defined in this PDS. Values may vary with shade.

Additional documents

Additional information is available at the Hempel website <https://www.hempel.com/service-and-support/technical-guidelines> or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.